

Applications

All position welding of offshore, shipbuilding, bridge construction machinery, and vehicles.

Characteristics on Usage

- ① SL-81Ni2 is a titania type Seamless flux cored wire for all position welding.
- ② It provides excellent notch toughness at low temperature.
- ③ It provides an exceptionally smooth and stable arc with a fast freezing slag system.

Notes on Usage

- ① Proper Preheating(50~150°C)(122~302°F) and interpass temperature must be used in order to release hydrogen which may cause cracking in weld metal when electoredes are used for medium and heavy plates.
- ② One-side welding defects such as hot cracking may occur with wrong welding parameter such as high welding speed.
- ③ Use 100%CO₂ gas.

Welding Position(All-Position)

Current

Shielding Gas



1G 2F 3G 4G

Typical Chemical Composition of All-Weld Metal (%)

C	Si	Mn	P	S	Ni
0.04	0.28	1.20	0.009	0.009	2.30

Typical Mechanical Properties of All-Weld Metal

YS MPa(lbs/in ²)	TS MPa(lbs/in ²)	EL (%)	Temp. °C (°F)	CVN-Impact Value J (ft · lbs)
570 (82,800)	620 (90,000)	22	-40 (-40)	90 (67)
			-60 (-76)	50 (37)

Approval

I Packing(Including Ball Pac)

Dia. (mm) 1.2 1.4
(in)

Spool(kg) 12.5
(lbs)

Sizes Available and Recommended Currents (Amp.)

Size mm (in)	1.2	1.4
F	130~300	160~330
V-up,OH	170~230	190~250
V-down	150~300	170~330