



Technical Data Sheet BrazeTec 2009



TD BT 0013 E.01

Standard

AG 206 acc. DIN EN 1044 (L-Ag20 acc. DIN 8513)
B-Cu44ZnAg(Si)-690/810 acc. ISO 3677

Nominal composition in wt.-% Ag 20; Cu 44; Zn 35,85; Si 0,15
Permitted impurities (weight-%):
Al 0,001; Bi 0,030; Cd 0,030; P 0,008; Pb 0,025; Total impurities 0,15

Technical data

Melting range	app. 690 - 810 °C (DIN EN 1044)
Working temperature	app. 810 °C
Density	app. 8,7 g/cm ³
Tensile strength acc. DIN 8525	with St 37: 380 MPa; with St 50: 430 MPa
Elongation	app. 25%
Electrical Conductivity	app. 10,6 m/ Ωmm ²
Operating temperature of brazed joint	max. 200 °C (without loss in strength)

Standard delivery form*

Wire: 1,0 - 1,5 - 2,0 mm Ø

Rods: 1,0 - 1,5 - 2,0 mm Ø, 500 mm length

Ribbon: 0,1/ 0,2/ 0,3/ 0,4 mm thickness and 70 mm width

Preforms: rings, shaped parts, sections, stamped and shaped parts, shims, discs, perforated plates

*Other delivery forms on request

Application

BrazeTec 2009 is a silver based brazing alloy with excellent flow characteristics. It can be used for brazing any steels, copper and copper based alloys as well as for nickel and nickel based alloys.

It can be used for brazing with flame or induction brazing procedures.

Typical applications are found e.g. in automotive and in the electric industry.

The information and statements contained herein are provided free of charge. They are believed to be accurate at the time of publication, but BrazeTec makes no warranty with respect thereto, including but not limited to any result to be obtained or the infringement of any proprietary rights. Use or application of such information or statements is at user's sole discretion, without any liability on the part of BrazeTec. Nothing herein shall be construed as a license of or recommendation for use which infringes upon any proprietary rights. All sales are subject to BrazeTec's General Conditions of Sale and Delivery.