



Technical Data Sheet

BrazeTec S 2



TD BT 0604 E.01

Standard

CP 105 acc. DIN EN 1044 (L-Ag2P acc. DIN 8513)
B-Cu92PAg-645/825 acc. ISO 3677

Nominal composition in wt.-% Cu remainder; Ag 2; P 6,3

Permitted impurities (weight-%):

Al 0,01; Bi 0,030; Cd 0,025; Pb 0,025; Zn 0,05; Zn + Cd 0,05; Total impurities 0,25

Technical data

| | | |
|---------------------------------------|----------------------------------------|---------------|
| Melting range | app. 645 - 825 °C | (DIN EN 1044) |
| Working temperature | app. 740 °C | (DIN EN 1044) |
| Density | app. 8,1 g/cm ³ | |
| Tensile strength acc. DIN 8525 | with Cu: 250 MPa | |
| Elongation | app. 5 % | |
| Electrical Conductivity | app. 4,0 m/ Ωmm ² | |
| Operating temperature of brazed joint | max. 150 °C (without loss in strength) | |

Standard delivery form*

Wire: 1,0 - 1,5 - 2,0 mm Ø

Rods: 1,5 - 2,0 - 3,0 mm Ø, 500 mm length

Ribbon: 0,1/ 0,2/ 0,3/ 0,4 mm thickness and 70 mm width

Preforms: rings, shaped parts, sections, stamped and shaped parts, lamina, discs, perforated plates

*Other delivery forms on request

Application

BrazeTec S 2 is a phosphorous-containing brazing alloy with good flow characteristics. The brazing alloy is suitable for joining copper to copper or copper-based materials. Due to its phosphorous content, you have not to use an additional flux for brazing only copper to copper. This brazing alloy is not allowed to be used if sulfur containing medias may have contact with the joint during operating. Further it is not allowed to use this alloy for joining steels (Fe) or materials containing iron, nickel and cobalt as brittle phases will be formed in the joint.

In refrigeration and air conditioning industries BrazeTec S 2 can be used for service temperatures down to -50°C.

It can be used for brazing with flame, with induction heating and in a furnace under protective atmospheres.

Typical applications are found e.g. in the electric industry and for the refrigeration and air conditioning industry.

The information and statements contained herein are provided free of charge. They are believed to be accurate at the time of publication, but BrazeTec makes no warranty with respect thereto, including but not limited to any result to be obtained or the infringement of any proprietary rights. Use or application of such information or statements is at user's sole discretion, without any liability on the part of BrazeTec. Nothing herein shall be construed as a license of or recommendation for use which infringes upon any proprietary rights. All sales are subject to BrazeTec's General Conditions of Sale and Delivery.