

E Alloy HX

CATEGORY SMAW Stick Electrodes

CLASSIFICATION

AWS	A 5.11: E NiCrMo-2
EN ISO	14172:
DIN: W.Nr.	2.4665
DIN	1736:

SUITABLE FOR

Hasteloy X, and simmlar NiCrMo alloys, dissimilar welding of Nickel alloys, stainless steel, carbon steel and low alloyed steels.
 Excelent oxidation resistance at high temperatures upto 1200 degrees Celsius.