

## NiFe 55

**CATEGORY** GMAW-GTAW Solid wires

**TYPE** Nickel iron MIG wire for joining dissimilar materials and cast iron.

**APPLICATIONS** Suitable for welding stainless steels containing 12-14 Cr. Also for welding mild and low alloy steels which are exposed to temperatures up to 450C. Cast Iron repairs, rebuilding shafts, wheels, critical joints between steel and cast iron etc.

**PROPERTIES** Nickel Iron based filler metal for joint welding and claddings on cast Iron. Very well suited also for dissimilar welding between cast iron and high alloyed stainless and heat resistant steels or mild steels. Excellent Weldability with extreme crack resistance with a ductile weld deposit. Good welding and wetting characteristics and high resistance against porosity. The weld metal is corrosion and heat resistant. Very well suitable for welding with robotics or automated processes.

**CLASSIFICATION**

AWS	A 5.15: E NiFe-C1
EN ISO	1071: SC NiFe-1
DIN: W.Nr.	2.4472
DIN	1736:

**SUITABLE FOR** Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.

**APPROVALS** CE approved

**WELDING POSITIONS:**



**WELD METAL ANALYSIS %**

C	Ni	Fe
1.5	55	rest

**MECHANICAL PROPERTIES**

Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			Hardness HB 30
				-20°C	-40°C	-60°C	
AW	~220	~420					185

AW: as welded

**WELDING PARAMETERS / PACKING**

D (mm)	Welding Parameters		spooling type	Packing	
	Voltage (V)	Current (A)		kg / spool	kg / pallet
0.8	15-25	110-220	K-300	15	
1.0	18-28	150-260	K-300	15	
1.2	20-30	180-300	K-300	15	

**REDRYING TEMPERATURE** not required