

SA 307

CATEGORY SAW Arc Submerged

CLASSIFICATION
AWS A 5.9: ER 307
EN ISO 14343-A: S 18 8 6
DIN: W.Nr. 1.4370

SUITABLE FOR Buffer layers before hardfacing, armor plate, (type 409, 304), high Manganese austenitic steel, heterogeneous welding, difficult to weld steels such as: 42CrMo4, C45, 42MnV7, tool steels etc.