



**W.A. ALLOY CO.**

WASHINGTON ALLOY'S Quality  
Management System is  
Certified to ISO 9001:2008  
Cert # 05-R0925

# USA 70S-B2L

(Previously ER80S-B2L by AWS)

## Welding Wire and Rod

U.S. ALLOY CO.  
dba Washington Alloy  
7010-G Reames Rd.  
Charlotte, NC 28216  
[www.weldingwire.com](http://www.weldingwire.com)



**American Welding Society**  
Sustaining Company Member



### ALLOY DESCRIPTION AND APPLICATION;

70S-B2L is a low alloy filler designed to produce high strengths on 1 1/4 & Cr -1/2 Mo steels found in high temperature/high pressure piping and vessels. This alloy is identical to the ER80S-B2 except it has a lower carbon content maximum that may lower the strength & hardness and exhibits greater resistance to cracking and used more often when welds are left in the as-welded condition. May also be used on carbon steels to Cr-Mo base metals. Controlled preheat, interpass and postheat treatment may be needed to avoid cracking.

### TYPICAL GMAW WELDING PROCEDURES; DCEP Short Circuit <sup>(1)</sup> 98Ar/2% O<sub>2</sub>

Wire Diameter	Wire Speed (ipm)	Amps	Volts	Travel speed (ipm)	75/25 CO <sub>2</sub> (cfh)
0.023	80-350	30-85	14-19	10-15	20-25
0.030	110-340	40-130	15-20	12-24	20-25
0.035	100-520	60-235	16-25	11-40	20-30
0.045	70-270	90-290	18-23	12-22	25-35
<i>Spray 0.035</i>	<i>320-600</i>	<i>160-300</i>	<i>23-26</i>	<i>11-22</i>	<sup>(1)</sup> <i>25-35</i>
<i>0.045</i>	<i>170-550</i>	<i>170-375</i>	<i>23-29</i>	<i>12-21</i>	<sup>(1)</sup> <i>25-35</i>
<i>1/16"</i>	<i>175-350</i>	<i>275-475</i>	<i>25-31</i>	<i>9-19</i>	<sup>(1)</sup> <i>25-35</i>

### TYPICAL GTAW WELDING PROCEDURES; DCEN with EWTh-2 truncated conical tip

Filler Wire Size	Tungsten	Amps	Volts	Gas Cup Size	Argon (cfh)	Base thickness
1/16"	1/16"	100-160	12	3/8"	20	1/16-3/32"
1/16-3/32"	3/32"	120-250	12	3/8"	20	1/8- 3/16"
1/8"	1/8"	150-300	12	1/2"	25	1/4-1/2"

Procedures may vary with change in position, base metals, filler metals, equipment and other changes.

### WIRE CHEMISTRY (%) AND WELD METAL PROPERTIES; PWHT

	AWS Spec.		AWS Spec
Carbon	0.05 max	Tensile Strength (psi)	75,000 min.
Manganese	0.40-0.70	Yield Strength (psi)	58,000 min.
Silicon	0.40-0.70	Elongation in 2"	19% min.
Phosphorus	0.025 max	Chromium	1.20-1.50
Sulfur	0.025 max	Copper	0.35 max
Molybdenum	0.40-0.65	Nickel	0.20 max

### AVAILABLE SIZES:

TT 70S-B2L = Cut lengths of 1/16, 3/32, 1/8  
Other sizes available – please inquire

**SPECIFICATIONS;** ANSI/AWS A5.28 ER 70S-B2L

ASME SFA 5.28 ER 70S-B2L ; A-3, F-6

**EAST COAST**  
7010-G Reames Rd  
Charlotte, NC 28216  
Tel (888) 522-8296  
Fax (704)598-6673

**GULF COAST**  
4755 Alpine Drive #100A  
Stafford, TX 77477  
Tel (877) 711-9274  
Fax (281)313-6332

**WEST COAST**  
8535 Utica Ave  
Rancho Cucamonga, CA 91730  
Tel(800)830-9033  
Fax (909)291-4586



2012 DC

Warehouse Distribution Center – Dayton, Ohio

Head Office – Puyallup, Washington

Washington Alloy Company believes that all information and data given is correct. Use this information to assist in making your own evaluations or decisions and this information should not be mistaken as an expressed or implied warranty. U.S. ALLOY CO. assumes no liability for results or damages incurred from the use of any information contained herein, in whole or in part.